

UHMWPE POROUS MATERIAL

SUNMAP LC

Features

- As SUNMAP is a porous sintered material having an open-cell structure; it offers the excellent air and moisture permeability.
- As SUNMAP is made of porous UHMWPE having high wear resistance and low friction coefficient the slip properties of SUNMAP is enhanced.
- SUNMAP offers good chemical resistance against typical acids and alkalis.
- Base Grade

Structure



Fig. 1

Properties

Table 1. General Properties

Item	Unit	Characteristic value						Test method
		0.1	0.2	0.3	0.5	1.0	2.0	
Thickness	mm	0.1	0.2	0.3	0.5	1.0	2.0	—
Air permeability	cm ³ /cm ² /sec	21	8	7	1.4	0.5	0.2	JIS L1096
Pore size	μm	17						—
Porosity	%	30						—
Tensile strength	MPa	12						JIS C2107
Elongation	%	90						JIS C2107
Hardness	Shore D	48						ASTM D2240
Surface Roughness (Ra)	μm	2.0						JIS B 0601
Coefficient of kinetic friction	—	0.1						JIS K7125
Surface resistance	Ω/□	> 10 ¹³						JIS K7194

 1/2
 LC_02E

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.

Product size

Table 2 Sheet type

Thickness(mm)	Width(mm)	Length(mm)
0.1	100~700	100~1200
0.2		
0.3		
0.5		
1.0	100~500	100~500
2.0		

Table 3 Roll type

Thickness(mm)	Width(mm)	Length(m)
0.1	100~700	10
0.2		
0.3		
0.5		

Applications

- In ceramic condenser manufacturing process, SUNMAP is used as “shock-absorber”.
- In LCD manufacturing process, SUNMAP is used as “shock-absorber”.

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications described in these documents. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission. Contact details are provided at the end of this document. Please do not hesitate to contact us for any inquiry.